

SECTION 201 – 6” LIME TREATED SUBGRADE

1. GENERAL

When so specified in this section, materials, equipment and Construction shall conform to Special Provision 90P-141-R1 to the 1990 Edition of the Standard Specifications for State Road and Bridge Construction as published by the Kansas Department of Transportation, hereinafter referred to as the “Special Provision”. This work shall consist of mixing soil and hydrated lime slurry in accordance with the Special Provision, as shown on the Plans or established by the Engineer.

The use of “Pebble-Quick” lime will be permitted as an alternate method of subgrade treatment. All noted application rates will apply.

2. MATERIALS

Materials shall conform to the requirements specified in the Materials Division.

Hydrated Lime	Section 2000
Water	Section 2400

3. RATES OF APPLICATION

Rates of application shall be as follows:

Hydrated Lime – 5.00% by weight of the top 6” of soil *
Water – 30.00 % by weight of the top 6” of soil *

*(Soil @ 110 lbs./cubic foot)